

# KEY URECON CV

## Product Information Sheet



## DESCRIPTION

**KEY URECON CV** is a heavy duty, trowel applied urethane modified cementitious topping formulated for vertical applications. **KEY URECON CV**'s high impact resistance and excellent thermal shock and chemical resistance make it ideal for heavy manufacturing and food processing areas. **KEY URECON CV** is a moisture vapor tolerant system making it the ideal solution for many moisture problems. **KEY URECON CV** may be used both indoors and outdoors and in areas where freeze/thaw is a factor. Excellent for forming cove base, cants and trench linings, **KEY URECON CV** is the key choice for wet areas, dairies, food processing areas, and industrial kitchens.

## KEY ADVANTAGES

- High impact, thermal shock, and wear resistance
- Excellent chemical resistance
- Low odor for use in occupied areas
- Meets USGBC LEED criteria for low VOC
- Hygienic—will not support growth of fungus or bacteria
- Moisture vapor tolerant system; up to 95% RH probe test and 15 lbs calcium chloride test
- Chemical resistant sealers are available
- Meets USDA requirements
- Rapid one step application for fast return to service

## KEY CONSIDERATIONS

- Should be applied when temperature is between 50°F and 85°F
- Site must be free from condensation or water contamination during application and cure
- Concrete substrate must be free of dirt, waxes, curing agents, and other foreign materials
- Expansion joints in the substrate must be revealed through the topping and filled with urethane sealant
- Movement of substrate cracks may transmit through system

## COLOR SELECTION

Refer to **Key Dry Oxide Pigment Colors Chart**. Price surcharge for Dark/Light Blue, Green. May also use **Key Urethane Pigment Packs** at additional cost. Light colors may become altered with exposure to UV spectrum light.

## CURE/DRY TIME

Working Life	10-15 mins @ 75°F, 50% RH
Recoat* (*Accelerator Additive reduces time)	6-8 hrs @ 75°F, 50% RH
Light Foot Traffic Service	8-10 hrs @ 75°F, 50% RH
Light Vehicular Traffic	12-16 hrs @ 75°F, 50% RH
Full Cure & Max. Resistance	3-5 days @ 75°F, 50% RH

## APPLICATION

### SURFACE PREPARATION

Surface Preparation is the most critical portion of any successful resinous flooring system application. All substrates must be properly prepared as outlined in **Key Resin Technical Bulletin #1**. Work must be performed by trained or experienced contractors or maintenance personnel. The **Key Resin Technical Service Department** is available to answer any questions.

### MIXING INSTRUCTIONS

Mechanical mixing is required. Add Part I and Part II in running mixer and blend until uniform (about 30 seconds). Add Part III aggregate and pigment pack slowly to mix and blend for 1 more minute. Use immediately.

### INSTALLATION

**KEY URECON CV** is installed using a steel cove trowel or flat trowel depending on the application. Refer to detailed installation instructions document and **Key Resin Technical Service** for additional important details.

### CLEAN UP

Clean skin with soap and water. Tools and equipment should be cleaned with xylene or lacquer thinner. Consult Safety Data Sheet (SDS) for safety and health precautions.

## MAINTENANCE

After completing the application of **KEY URECON CV**, the installer should provide the owner with maintenance instructions. **KEY URECON CV** is easily cleaned with neutral soaps or detergents. Refer to **Key Resin Technical Bulletin #3** and **#3A** for additional recommendations.

## COMPOSITION

**KEY URECON CV** is a urethane modified, portland cement system blended with a variety of graded silica, or ceramic fillers.

# KEY URECON CV

## Product Information Sheet



### TECHNICAL DATA

Mixing Ratio	Pre-Packaged Kit
Weight (liquids)	9.00-9.50 lbs per gallon, mixed
Volatile Organic Content (VOC) (EPA Method 24)	0 g/L, compliant to low VOC Rule 1113 in all 50 states

### AVAILABILITY

**Key Resin** materials are available throughout the United States, Canada, and a number of other countries. Contact the **Key Resin Representative** in your area for details.

### TECHNICAL SERVICE

**Key Resin Company** provides services and consultations on material selection, specification, troubleshooting, and other information on the proper repair and protection of concrete surfaces. **Key Resin Sales/Technical Representatives** are available to assist you. Telephone 888.943.4532 or visit [www.keyresin.com](http://www.keyresin.com).

### PHYSICAL PROPERTIES

Compressive Strength	ASTM C579	7,500 psi
Tensile Strength	ASTM C307	800 psi
Flexural Strength	ASTM C580	2,000 psi
Fungus and Bacteria Growth	MIL-F-52505 § 4.4.2.11	Will not support growth of fungus or bacteria when subjected to mildew and bacteria tests
Thermal Coefficient of Expansion	ASTM C531	1 x 10 <sup>-5</sup> in/in/per °F
Impact Resistance	MIL-F-3134J	Withstands 16 ft./lb. without cracking, delamination, or chipping
Modulus of Elasticity	ASTM C469	1.7 x 10 <sup>5</sup> psi
Adhesion to Concrete	ASTM D7240	300-400+ psi (Concrete Failure, varies by concrete strength)
Service Temperature Resistance		-50 – 240°F wet, 280°F wet intermittent, 350°F dry
Thermal Shock Resistance	ASTM C884	Passes

### WARRANTY

**Key Resin Company** ("Key") warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed, and applied in accordance with recommendations of Key. If any product fails to meet this warranty, the liability of Key will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Key within (1) one year of delivery of materials. Key may in its discretion refund the price received by Key in lieu of replacing the material. No customer, distributor, or representative of Key is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Key. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Key reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. KEY'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND KEY SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.